


## FILTER PAPERS

Technical Sheet

CL-501

Weight	70 [g/m <sup>2</sup> ]
Thickness	0,16 [mm]
Filtration speed	22 [s]
Surface	smooth
Ash content	< 0,1 (%)
Average retention capacity	4 - 12 [μm]



### **Applications and properties**

Medium fast filtration, for general laboratory use.

These data are typical values and must not be regarded as specification.