


FILTER PAPERS

Technical Sheet

CN-544

Weight	85 [g/m ²]
Thickness	0,2 [mm]
Filtration speed	55 [s]
Surface	smooth
Ash content	< 0,01 (%)
Average retention capacity	4 - 7 [μm]



Applications and properties

Ashless, medium fast filtration, e.g. for magnesium ammonium phosphate, zinc sulphide, etc.

These data are typical values and must not be regarded as specification.